



ENDURO CLASSIC PLUS 200 J

satin 6925, 205 g/m²

Tear-resistant paper. Ideal for tear-resistant hang tags, folders, indexes and documents.

ENDURO Classic Plus 200 J is a tear-resistant composite material consisting of a 40 µm PP film core and white, natural satin-finished paper surfaces. The three-layer product structure is durable, resistant to edge tearing and water impermeable. It can be cut, punched, perforated, drilled, embossed, scored, folded, glued and bound without issue.

The super-calendered, extra-smooth paper surfaces offer optimized feed properties and printing results. Thanks to the highly absorbent surfaces, all common standard inks and varnishes can be used in offset and flexo printing. Suitable for laser printing and variable thermal transfer and dot matrix printing. With excellent drying and ink/toner adhesion. Can be stamped easily and lettered manually.

Thanks to the multi-layer product structure ENDURO offers an affordable, eco-friendly and sustainable alternative to fully synthetic media. It is PVC-free and FSC®-certified.

Advantages

- Tear-resistant
- High fold strength
- Water impermeable
- Excellent printability
- FSC®-certified
- PVC-free



General tips

For quality reasons ENDURO should be stored originally packed. Storage & converting conditions of 20±5°C and 50±10% rel. humidity are recommended.

Food contact

Please inform us whenever intended use is linked to food contact.

It may be possible to provide a Declaration of Compliance confirming material suitability for your specific application.

Waste disposal

ENDURO Classic Plus 200 J has been awarded a recyclability certificate by the Cyclo-HTP Institute. According to this certificate, the majority of the paper fibres (73% of the total composite) can be recovered in the paper recycling process. The film is separated and can be used for thermal energy recovery. When sorted using near-infrared sensors (NIR), this product is identified as paper and assigned to the paper stock stream for recycling. It can therefore be disposed of both via the recycling path for waste paper and via the recycling path for lightweight packaging.

In the recycling path for waste paper, it is classified as "Mixed waste paper, grade 5.01" according to EN 643. In the path for light packaging (LVP), it is classified as "PPK (paper, cardboard, carton) from LVP, fraction no. 550".

As conversion (i.e. printing) may significantly change the characteristics of a product, these recycling recommendations may only apply to ENDURO material before processing.

Technologies



Properties



Physical data

Name	Value	Tolerance	Norm
Weight [g/m ²]	205	±20	ISO 536
Thickness (total) [µm]	215	±15	ISO 534
Bending stiffness MD [mN]	> 870		ISO 2493-1; 15°/10mm
Bending stiffness CD [mN]	> 450		ISO 2493-1; 15°/10mm
Tensile strength MD [N/15mm]	> 180		ISO 1924-3/2/300
Tensile strength CD [N/15mm]	> 180		ISO 1924-3/2/300
ISO Brightness, front side [%]	> 85		ISO 2470-1
ISO Brightness, reverse side [%]	> 85		ISO 2470-1
Whiteness, CIE, D65/10°, front side	> 100		ISO 11475
Whiteness, CIE, D65/10°, reverse side	> 100		ISO 11475
Opacity [%]	> 96		ISO 2471

Durability

Originally packed under recommended storage conditions ENDURO rolls and sheets can be stored for at least 3 years.

Printing instructions

Detailed recommendations for printing and processing of ENDURO can be found under [Download](#).