

GREENGRAFX TRISOLV PRIME 135 BB P-CA GLOSSY

glossy 3683, 135 g/m²

Sustainable, self-adhesive paper with blue backing for poster and promotional applications.

GreenGraFX TriSolve Prime BB is ideal for environmentally friendly billboards and exhibition walls. The PVC-free, weather and water resistant paper is suitable for printing with solvent, latex and UV-curable inks. The water-based permanent acrylic adhesive adheres to almost all smooth, clean surfaces, allowing the material to be used in a variety of ways. The blue backing provides excellent coverage of the substrate and best opacity. Thanks to the scratch-resistant surface, the product can be used indoors for long-term advertising. Outdoors, the material is recommended for short- to medium-term applications.

Technologies



Properties



Advantages

- Brilliant colour reproduction
- Water-repellent surface
- Blueback ensures good cover of substrates
- High colour saturation saves up to 30% of printing inks
- Adheres to clean and smooth surfaces
- FSC® certified front material
- PVC free

General tips

- Please note when printing with any of the 300 and 500 series HP Latex printer, to print roll to roll!
- The ink amounts must be adjusted to the paper. Please reduce the single colors cyan, magenta, yellow and black (ink restrictions) and shorten the maximum amount of ink (ink limit). This will help your costs on inks and improve your drying performance.
- Please follow the recommendations of the printer and ink manufacturer. The temperature for preheating and drying the media should be checked previously to make sure you will achieve desired results.
- To maintain the high quality of the paper, it should be stored and converted in a climate of 30 – 65 % relative humidity and at a temperature of 10 – 30 °C (50 – 86 °F).
- Latex / IR hardening ink is not fully water-resistant.

Physical data

Name	Value	Norm
Weight (without liner/ adhesive) [g/m ²]	135	ISO 536
Weight [g/m ²]	245	ISO 536
Thickness (paper) [μm]	210	ISO 534
Thickness (paper without liner / adhesive) [μm]	150	ISO 534
Opacity [%]	> 98	ISO 2471
Chromaticity (D50/2°) a* M0	L*95.0 a*1.0 b*-3.5	ISO 13655, M0
Adhesion strength on glass (24h) [N/25mm]	20	FTM 1
Adhesion strength on V2A (24h) [N/25mm]	25	FTM 1
Adhesion strength on Forex (24h) [N/25mm]	20	FTM 1
Base	TriSolv Billboard Paper Prime 135 Glossy 3682	